

IN THE SPECIFICATION

Please amend paragraph [0029] as indicated:

[0029] The composition further includes a chain extender having a backbone chain with from two to eight carbon atoms. The backbone chain is preferably from two to six carbons. The chain extender also has a weight-average molecular weight of less than 1,000. Preferably, the chain extender has a weight-average molecular weight of from 25 to 250 and more preferably less than 100. The chain extender preferably has a hydroxyl number of ~~from about 448 to about 4,488~~ greater than 450 mg KOH/g to provide desired viscoelastic properties. The chain extender may be present in an amount of from 5 to 50 parts by weight based on 100 parts by weight of the composition and preferably from 5 to 30 parts by weight based on 100 parts by weight of the composition, and more preferably 5 to 15.